

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 955 325 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
10.11.1999 Bulletin 1999/45

(51) Int Cl.⁶: **C08G 8/34**, C09D 11/10

(21) Application number: **99401121.1**

(22) Date of filing: **07.05.1999**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **08.05.1998 US 74751**

(71) Applicant: **WESTVACO CORPORATION**
New York New York 10017 (US)

(72) Inventor: **Matzinger, Michael D.**
Mt. Pleasant, SC 29464 (US)

(74) Representative: **Portal, Gérard et al**
Cabinet Beau de Loménie
158, rue de l'Université
75340 Paris Cédex 07 (FR)

(54) **Rosin-modified phenolic resin compositions, their preparation and uses**

(57) This invention relates to novel phenolic rosin resins and the process for preparing them. In particular, the invention relates to novel phenolic rosin resin com-

positions which exhibit properties that make them useful in formulating vehicles for lithographic printing inks and other coating applications.

EP 0 955 325 A1

Description

FIELD OF THE INVENTION

[0001] This invention relates to novel phenolic rosin resins and the process for preparing them. In particular, the invention relates to novel phenolic rosin resin compositions which exhibit properties that make them useful in formulating vehicles for lithographic printing inks and other coating applications.

BACKGROUND OF THE INVENTION

[0002] Lithographic inks consist primarily of pigments, natural and/or synthetic resins with high melting points (100°C to 200° C.), alkyd resins, and hydrocarbon solvents. Low concentrations of plasticizers, antioxidants, chelates, pH modifiers, antiskinning agents, and other additives also are included in lithographic ink formulations.

[0003] The natural and synthetic high-melting resins are typically either petroleum-derived or wood-derived. Used solely or in combination, these resins are dissolved in the high-boiling hydrocarbon solvents to give homogenous systems well known in the art as varnishes. Varnishes usually contain 20 to 70% resin solids. The alkyds, plasticizers, antioxidants, etc. are often included in the varnish, so that solids levels may exceed 70%.

[0004] It is known to those skilled in the art that in order to prepare phenolic resins, rosin may be reacted with phenols and formaldehyde to give phenol-rosin condensates which contain reactive double bonds and which may be reacted further in Diels-Alder and/or "ene"-addition fashion with alpha, beta-unsaturated carbonyl compounds. These Diels-Alder and ene adducts of phenol-rosin condensates are then esterified with polyols to give broad molecular weight distribution resins with low residual acid numbers. The traditional methods of producing such phenolic rosin resins are well-known. Generally, the rosin is first heated (to around 180°C) and melted. Thereafter the temperature is reduced (to around 115°C), phenol and formaldehyde are added, and the mixture is reacted in a phenol-condensate reaction over a period of time (normally around two hours). The resulting product is held under pressure for about two hours, then vented. The temperature is subsequently elevated to about 195°C, maleic anhydride (or the like) is added, and the resulting mixture is maintained at temperature for around an hour and a half. Thereafter a polyol is added to the mixture, the temperature is increased to about 275°C and maintained for eight to ten hours in order to produce the phenolic rosin resin.

[0005] Phenolic resins must meet with several general requirements to be useful as lithographic ink resins. In order to make varnishes, for example, they must be capable of being dissolved in high-boiling hydrocarbon

solvents to yield clear varnishes with manageable viscosities for easy workability. The varnishes must be stable in storage to viscosity, color, and clarity changes. On paper, the resin in the varnish or finished ink must dry to yield a durable, smooth, and uniform film with good resistance to abrasion and chemicals.

[0006] Moreover, it is appreciated that for phenolic resins to be useful as dispersing resins in lithographic ink pigment processing operations such as flushing, the resins must exhibit several specific properties in addition to the aforementioned requirements general to all lithographic ink resins. For example, when mixed with highly aqueous pigment presscake in high torque dough mixers commonly used for flushing operations, the resins present in the lithographic ink varnish must exhibit excellent pigment wetting properties. Such properties lead to rapid and thorough coverage of pigment particles present in the presscake and to the concurrent displacement of water originally bound to or entrained in the particle aggregates and agglomerates. Good wetting properties also lead to strong adhesion of resin to particle surfaces so that, as aggregates and agglomerates are broken down into primary particle units, resin will coat the particle surfaces thereby providing a steric barrier to particle-particle reaggregation and reagglomeration. Strong adhesion to and thorough coverage of surfaces of primary particle units by resin thus leads to increased color strength, gloss, and transparency, as well as reduced bronzing in the resulting pigment concentrate.

[0007] However, major problems exist with the traditional methods of producing phenolic rosin resins. For example, the condensation reactions associated with these methods often result in excessive foaming. Such foaming can lead to spillages and the release of excessive amounts of aldehyde vapors into the atmosphere. While it is a common practice in the industry to employ anti-foaming agents in an attempt to control this problem, the use of such agents adds to the cost of the process. Moreover, these agents often cause printing inks formulated with the resulting phenolic rosin resin compositions to have adhesion problems (which are known in the industry as "fish eyes").

[0008] Another problem associated with these methods is that the phenolic condensation reaction temperatures must be maintained above about 110°C. Should the temperatures drop below this level, the rosin can crystallize - thereby forming a gel and rendering the mixture unusable. Yet a further problem associated with these traditional methods is the excessive cycle times caused by the necessity of adding the aldehyde at a controlled rate.

[0009] Therefore, an object of this invention is to solve these major problems by disclosing an improved method of producing phenolic rosin resin compositions that exhibit properties which makes them useful in formulating vehicles for lithographic printing inks and other coating applications.

[0010] A further object of this invention is to produce

novel phenolic rosin resin compositions which can be employed in varnishes for use in formulating lithographic printing inks.

SUMMARY OF THE INVENTION

[0011] The objects of this invention are met by producing phenolic rosin resin compositions via an improved method wherein a compound is added to the process which both a) functions as a solvent during the phenolic-rosin condensation reaction, and b) can function as a crosslinker during the esterification reaction. The present method permits the practitioner to conduct the phenolic-rosin condensation reactions at lower temperatures. This ability to lower the reaction temperatures allows one to avoid the traditional foaming problems, thereby reducing: a) the cost of the process (by eliminating the need for anti-foaming agents and decreasing energy costs), and b) the amount of aldehyde emissions released into the atmosphere. Moreover, the present method produces novel phenolic rosin resin compositions which exhibit unique chemical and physical properties well-suited for the production of varnishes for use in formulating printing inks.

DESCRIPTION OF THE PREFERRED EMBODIMENT

[0012] The improved method for producing novel phenolic rosin resin compositions comprises:

A) reacting in a condensation reaction:

- 1) about 30% to about 95% by total weight of the reactants of a rosin;
- 2) about 1% to about 40% by total weight of the reactants of a phenol; and
- 3) about 1% to about 25% by total weight of the reactants of an aldehyde, an aldehyde precursor and notably an aldehyde polymer including a straight or branched or cyclic chain;

at a temperature in the range of about 80°C to about 180°C for a period of time sufficient to produce phenol-rosin condensate, wherein the improvement comprises the addition of about 2% to about 50% by total weight of the reactants of a crosslinkable compound to the condensation reaction and wherein said crosslinkable compound functions as a solvent during the condensation reaction; and

B) reacting in an esterification reaction:

- 1) about 85% to about 99% by total weight of the reactants of the phenol-rosin condensate; and
- 2) about 1% to about 15% by total weight of the reactants of a crosslinkable compound;

at a temperature in the range of about 190°C to

about 290°C for a period of time sufficient to produce a phenolic rosin resin composition having an acid number no greater than 35.

5 [0013] Another embodiment of the improved method for producing novel phenolic rosin resin compositions comprises:

A) reacting in a condensation reaction:

- 1) about 50% to about 80% by total weight of the reactants of a rosin;
- 2) about 5% to about 25% by total weight of the reactants of a phenol; and
- 3) about 5% to about 15% by total weight of the reactants of an aldehyde, an aldehyde precursor and notably an aldehyde polymer including a straight or branched or cyclic chain;

at a temperature in the range of about 80°C to about 180°C for a period of time sufficient to produce phenol-rosin condensate, wherein the improvement comprises the addition of about 10% to about 20% by total weight of the reactants of a crosslinkable compound to the condensation reaction and wherein said crosslinkable compound functions as a solvent during the condensation reaction; and

B) reacting in an esterification reaction:

- 1) about 90% to about 95% by total weight of the reactants of the phenol-rosin condensate; and
- 2) about 5% to about 10% by total weight of the reactants of a crosslinkable compound;

at a temperature in the range of about 190°C to about 290°C for a period of time sufficient to produce a phenolic rosin resin composition having an acid number no greater than 35.

[0014] Where needed, an additional reaction may be added to the method in order to increase the molecular weight of the phenolic rosin resin compositions (thereby permitting the subsequent formulation of inks with desired properties, which comprises:

C) reacting in an addition reaction:

- 1) about 75% to about 99% by total weight of the reactants of the phenolic rosin resin composition; and
- 2) about 1% to about 25% by total weight of the reactions of a dienophile;

at a temperature in the range of about 100°C to about 250°C for a period of time sufficient to produce a dienophile-modified phenolic rosin resin composition.

[0015] An additional embodiment of the reaction that may be added to the method in order to increase the molecular weight of the phenolic rosin resin compositions (thereby permitting the subsequent formulation of inks with desired properties), which comprises:

C) reacting in an addition reaction:

- 1) about 85% to about 95% by total weight of the reactants of the phenolic rosin resin composition; and
- 2) about 5% to about 15% by total weight of the reactions of a dienophile;

at a temperature in the range of about 100°C to about 250°C for a period of time sufficient to produce a dienophile-modified phenolic rosin resin composition.

[0016] It should be noted that the order of reaction in the present method may be varied in order to produce phenolic rosin resin compositions and/or dienophile-modified phenolic rosin resin compositions with desired characteristics. Such a rotation of the reactions is well within the ability of one skilled in the art.

[0017] The key to the novel method is the employment of a crosslinkable compound which has the ability to both: a) function as a solvent at the lower temperatures associated with the phenol-rosin condensation reaction and b) function as a crosslinker when subjected to the higher temperatures associated with the esterification reaction. Crosslinkable compounds which are suitable for use in the present method should be liquid at the temperature at which the aldehyde is added to the process. Such crosslinkable compounds include polyols, polyamines, ethanolamines, combinations thereof, and the like. Polyols which are suitable for use as crosslinkable compounds in the present method include, but are not limited to, the following: ethylene glycol, diethylene glycol, polyethylene glycol, glycerol, pentaerythritol, dipentaerythritol, sorbitol, and combinations thereof. Polyamines which are suitable crosslinkable compounds include, but are not limited to, the following: hexamethylenediamine, piperazine, 2-methyl-1,5-pentanediamine, 1,3-pentanediamine, 1,2-diaminocyclohexane, bis (hexamethylene) triamine, and combinations thereof. Ethanolamines which are suitable crosslinkable compounds include, but are not limited to, the following: monoethanolamine, diethanolamine, 3-aminobenzyl alcohol, triisopropanolamine, and combinations thereof. It is preferred to add from about 10% to about 20% by total weight of the reactants of a crosslinkable compound to the condensation reaction. It is also preferred to react from about 5% to about 10% by total weight of the reactants of a crosslinkable compound in the esterification reaction.

[0018] The period of time needed to produce the phenol-rosin condensate at a temperature of about 80°C to

about 180°C is commonly in the range of from about 30 minutes to about eight hours (with one to four hours being a normal time period). The preferred temperature range for producing the phenol-rosin condensate is from about 95°C to about 140°C.

[0019] It is known in the art that rosin (which chemically constitutes a mixture of polyunsaturated polycyclic carboxylic acids) may be modified by reaction with acrylic acid, methacrylic acid, fumaric acid and/or maleic anhydride to yield the resulting Diels-Alder cyclo-adducts or "one" reaction adducts. Rosins which are suitable for use in the present method include, but are not limited to, the following: tall oil rosin, wood rosin, gum rosin, and combinations thereof. It is preferred to react from about 50% to about 80% by total weight of the reactants of a rosin in the condensation reaction. Phenols which are suitable for use in the present method include, but are not limited to, the following: phenol, nonylphenol, octylphenol, bisphenol A, butyl phenol, and combinations thereof. It is preferred to react from about 5% to about 25% by total weight of the reactants of a phenol in the condensation reaction.

[0020] Aldehydes which are suitable for use in the present method include an aldehyde, an aldehyde precursor and notably an aldehyde polymer including a straight or branched or cyclic chain; and examples which are not limited to, the following: paraformaldehyde, formaldehyde, and combinations thereof.

[0021] In the specification and in the claims, aldehyde is used as a general term for aldehyde, aldehyde precursor and notably aldehyde polymer including a straight or branched or cyclic chain.

[0022] It is preferred to react from about 5% to about 15% by total weight of the reactants of an aldehyde in the condensation reaction.

[0023] Where desired, a catalyst may be employed in the phenol-rosin condensate reaction. Suitable catalysts include alkali metal hydroxides, alkali metal oxides, and the like. Where employed, it is preferred to use an amount of catalyst in the range of from about 0.01% to about 5.00% by total weight of reactants.

[0024] The period of time needed to produce the phenolic rosin resin composition at a temperature of about 190°C to about 290°C is usually in the range of from about one hour to about eight hours. The preferred temperature range for the esterification reaction is from about 220°C to about 265°C. It is further preferred to produce a phenolic rosin resin compound which exhibits an acid number no greater than 25.

[0025] Dienophiles which are suitable for use in addition reaction include alpha, beta unsaturated carbonyl compounds and the like. Specific dienophiles which are suitable for use in the present method include, but are not limited to, the following: maleic anhydride, fumaric acid, itaconic acid, itaconic anhydride, acrylic acid, crotonic acid, the alkyd esters of these compounds, and combinations thereof. It is preferred to react from about 85% to about 95% by total weight of the reactants of the

phenolic rosin resin composition and from about 5% to about 15% by total weight of the reactants of a dienophile in the addition reaction.

[0026] The period of time needed to produce the dienophile-modified phenolic rosin resin compositions at a temperature of about 100°C to about 250°C is usually in the range of from about fifteen minutes to about three hours (with about 45 to 90 minutes being a normal time period). The preferred temperature range for the addition reaction is from about 180°C to about 240°C.

[0027] As appreciated in the art, the exact components and properties of components desired for any coating application can vary and, therefore, routine experimentation may be required to determine the optional components and proportions of components for a given application and desired properties.

[0028] The invention also covers the phenolic rosin resin composition as well as a dienophile-modified phenolic rosin resin composition as obtainable by the above method.

[0029] The invention further covers a varnish for lithographic ink formulations comprising a dispersion of the phenolic rosin resin composition or of the dienophile-modified phenolic rosin resin composition.

[0030] The following examples are provided to further illustrate the present invention and are not to be construed as limiting the invention in any manner.

EXAMPLE 1

[0031] Into a flask equipped with an overhead stirrer, condenser, Dean Stark trap, thermocouple, nitrogen delivery system, and heating mantle, was charged 1000 grams of Rosin SS (a tall oil rosin commercially available from Westvaco Corporation) and 70 grams of glycerine. The contents were heated to a temperature of 100°C and 370 grams of nonylphenol, 60 grams of bisphenol A, 30 grams of t-butyl phenol, and 12 grams of magnesium oxide were added. Thereafter 136 grams of paraformaldehyde were added over a ten minute period. The temperature was maintained at 100°C for 30 minutes; after which the temperature was increased to 120°C and maintained for two hours. The temperature was subsequently increased to 220°C and water was collected. Thereafter 10 grams of pentaerythritol were added, the temperature was increased to 240°C and maintained for five hours. The resulting phenolic rosin ester composition (hereafter referred to as Composition A) had an acid number of 26 and a ring and ball softening point of 166°C.

[0032] Varnishes were produced using 33 wt. % of Composition A in 77 wt. % of alkaline refined linseed oil (ARLO). The varnishes had a viscosity of 1200 line-to-line seconds and a dilutability with Magesol M-47 oil (a hydrocarbon solvent commercially available from Magie Bros. Oil Co.) of 200%.

EXAMPLE 2

[0033] For evaluation purposes an attempt was made to produce a rosin resin using the procedure taught in example 1 above, except that no liquid polyol solvent (i. e., glycerine) was employed.

[0034] Into a flask equipped with an overhead stirrer, condenser, Dean Stark trap, thermocouple, nitrogen delivery system, and heating mantle, was charged 1000 grams of Rosin SS (a tall oil rosin commercially available from Westvaco Corporation) and 70 grams of glycerine. The contents were heated to a temperature of 100°C and 370 grams of nonylphenol, 60 grams of bisphenol A, 30 grams of t-butyl phenol, and 12 grams of magnesium oxide were added. Thereafter 136 grams of paraformaldehyde were added over a ten minute period. The temperature was maintained at 100°C for 30 minutes; after which the temperature was increased to 120°C and maintained for two hours. The temperature was subsequently increased to 220°C and water was collected.

[0035] At this point, the resin "gelled" and the synthesis was aborted.

EXAMPLE 3

[0036] Into a flask equipped with an overhead stirrer, condenser, Dean Stark trap, thermocouple, nitrogen delivery system, and heating mantle, was charged 1000 grams of Rosin SS. (a tall oil rosin commercially available from Westvaco Corporation), 57.5 grams of glycerine, 381.1 grams of nonylphenol, and 75 grams of bisphenol A. The contents were heated to a temperature of 115°C and 12 grams of magnesium oxide were added. Thereafter 136 grams of paraformaldehyde were added over a ten minute period. The temperature was maintained at 104°C for 30 minutes; after which the temperature was increased to 113°C and maintained for two hours. The temperature was subsequently increased to 200°C and water was collected. Thereafter 21 grams of pentaerythritol were added, the temperature was increased to 240°C and maintained for eight hours. The resulting phenolic rosin ester composition (hereafter referred to as Composition B) had an acid number of 30 and a ring and ball softening point of 148°C.

[0037] Varnishes were produced using 33 wt. % of Composition B in 77 wt. % of alkaline refined linseed oil (ARLO). The varnishes had a viscosity of 55 line-to-line seconds and a dilutability with Magesol M-47 oil (a hydrocarbon solvent commercially available from Magie Bros. Oil Co.) of 1136%,

EXAMPLE 4

[0038] Into a flask equipped with an overhead stirrer, condenser, Dean Stark trap, thermocouple, nitrogen delivery system, and heating mantle, was charged 1000 grams of Rosin SS (a tall oil rosin commercially available from Westvaco Corporation), 51 grams of L-5 Fatty Acid

(a tall oil-based fatty acid commercially available from Westvaco Corporation), 57.5 grams of glycerine, 381.1 grams of nonylphenol, and 75 grams of bisphenol A. The contents were heated to a temperature of 115°C and 12 grams of magnesium oxide were added. Thereafter the temperature was decreased to 105°C and 136 grams of paraformaldehyde were added over a ten minute period. The temperature was maintained at 104°C for 30 minutes; after which the temperature was increased to 113°C and maintained for two hours. The temperature was subsequently increased to 203°C and water was collected. Thereafter 21 grams of pentaerythritol were added, the temperature was increased to 240°C and maintained for eight hours. The resulting phenolic rosin ester composition (hereafter referred to as Composition C) had an acid number of 26 and a ring and ball softening point of 135°C.

[0039] Varnishes were produced using 33 wt. % of Composition A in 77 wt. % of alkaline refined linseed oil (ARLO). The varnishes had a viscosity of 69 line-to-line seconds and a dilutability with Magesol M-47 oil (a hydrocarbon solvent commercially available from Magie Bros. Oil Co.) of 1514%.

[0040] Many modifications and variations of the present invention will be apparent to one of ordinary skill in the art in light of the above teachings. It is therefore understood that the scope of the invention is not to be limited by the foregoing description, but rather is to be defined by the claims appended hereto.

Claims

1. An improved method for producing phenolic rosin resin compositions which comprises:

A) reacting in a condensation reaction:

- 1) about 30% to about 95% by total weight of the reactants of a rosin;
- 2) about 1% to about 40% by total weight of the reactants of a phenol; and
- 3) about 1% to about 25% by total weight of the reactants of an aldehyde, an aldehyde precursor and notably an aldehyde polymer including a straight or branched or cyclic chain;

at a temperature in the range of about 80°C to about 180°C for a period of time sufficient to produce a phenol-rosin condensate, wherein the improvement comprises the addition of about 2% to about 50% by total weight of the reactants of a crosslinkable compound to the condensation reaction and wherein said crosslinkable compound functions as a solvent during the condensation reaction; and
B) reacting in an esterification reaction:

- 1) about 85% to about 99% by total weight of the reactants of the phenol-rosin condensate; and
- 2) about 1% to about 15% by total weight of the reactants of a crosslinkable compound;

at a temperature in the range of about 190°C to about 290°C for a period of time sufficient to produce a phenolic rosin resin composition having an acid number no greater than 35.

2. The method of claim 1 which further comprises:

A) reacting in a condensation reaction:

- 1) about 50% to about 80% by total weight of the reactants of a rosin;
- 2) about 5% to about 25% by total weight of the reactants of a phenol; and
- 3) about 5% to about 15% by total weight of the reactants of an aldehyde, an aldehyde precursor and notably an aldehyde polymer including a straight or branched or cyclic chain;

at a temperature in the range of about 80°C to about 180°C for a period of time sufficient to produce a phenol-rosin condensate, wherein the improvement comprises the addition of about 10% to about 20% by total weight of the reactants of a crosslinkable compound to the condensation reaction and wherein said crosslinkable compound functions as a solvent during the condensation reaction; and
B) reacting in an esterification reaction:

- 1) about 90% to about 95% by total weight of the reactants of the phenol-rosin condensate; and
- 2) about 5% to about 10% by total weight of the reactants of a crosslinkable compound;

at a temperature in the range of about 190°C to about 290°C for a period of time sufficient to produce a phenolic rosin resin composition having an acid number no greater than 35.

3. The method of claim 1 or 2 which further comprises:

C) reacting in an addition reaction:

- 1) about 75% to about 99% by total weight of the reactants of the phenolic rosin resin composition; and
- 2) about 1% to about 25% by total weight of the reactants of a dienophile;

- at a temperature in the range of about 100°C to about 250°C for a period of time sufficient to produce a dienophile-modified phenolic rosin resin composition.
4. The method of any one of claim 1 to 3 which further comprises:
- C) reacting in an addition reaction:
- 1) about 85% to about 95% by total weight of the reactants of the phenolic rosin resin composition; and
- 2) about 5% to about 15% by total weight of the reactants of a dienophile;
- at a temperature in the range of about 100°C to about 250°C for a period of time sufficient to produce a dienophile-modified phenolic rosin resin composition.
5. The method of any one of claims 1 to 4 wherein the rosin is a member selected from the group consisting of tall oil rosin, wood rosin, gum rosin, and combinations thereof.
6. The method of any one of claims 1 to 5 wherein the phenol is a member selected from the group consisting of phenol, nonylphenol, octylphenol, bisphenol A, butyl phenol, and combinations thereof.
7. The method of any one of claims 1 to 6 wherein the aldehyde is a member selected from the group consisting of paraformaldehyde, formaldehyde, and combinations thereof.
8. The method of any one of claims 1 to 7 wherein the crosslinkable compound is a member selected from the group consisting of polyols, polyamines, ethanolamines, and combinations thereof.
9. The method of any one of claims 1 to 8 wherein the crosslinking compound is a member selected from the group consisting of ethylene glycol, diethylene glycol, polyethylene glycol, glycerol, pentaerythritol, dipentaerythritol, sorbitol, hexamethylenediamine, piperazine, 2-methyl-1,5-pentanediamine, 1,3-pentanediamine, 1,2-diaminocyclohexane, bis (hexamethylene) triamine, monoethanolamine, diethanolamine, 3-aminobenzyl alcohol, triisopropanolamine, and combinations thereof.
10. The method of any one of claims 1 to 9 wherein the condensation reaction is conducted at a temperature in the range of about 95°C to about 140°C.
11. The method of any one of claims 1 to 10 which further comprises adding from about 0.01% to about 5.00% by total weight of the reactants of a catalyst to the condensation reaction.
12. The method of claim 11 wherein the catalyst is a member selected from the group consisting of alkali metal hydroxides, alkali metal oxides, and combinations thereof.
13. The method of any one of claims 1 to 12 wherein the phenolic rosin resin composition has an acid number no greater than 25.
14. The method of any one of claims 3 to 13 wherein the dienophile is a member selected from the group consisting of alpha, beta unsaturated carbonyl compounds and combinations thereof.
15. The method of any one of claims 3 to 14 wherein the dienophile is a member selected from the group consisting of maleic anhydride, fumaric acid, itaconic acid, itaconic anhydride, acrylic acid, crotonic acid, the alkyd esters of these compounds, and combinations thereof.
16. A phenolic rosin resin composition as obtainable by the method according to any one of claims 1 to 15.
17. A varnish for lithographic ink formulations comprising a dispersion of a the phenolic rosin resin composition of claim 16.
18. A dienophile-modified phenolic rosin resin composition as obtainable by the method according to any one of claims 3 to 15.
19. A varnish for lithographic ink formulations comprising a dispersion of the dienophile-modified phenolic rosin resin composition of claim 18.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 40 1121

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X	US 5 021 538 A (CREWS EVERETT) 4 June 1991 (1991-06-04) * example 1 * * claim 1 * ---	1-19	C08G8/34 C09D11/10
X	EP 0 769 538 A (HOECHST AG) 23 April 1997 (1997-04-23) * examples 1,7 * * claim 9 * ---	1-19	
X	US 4 643 848 A (THOMAS JOHN H ET AL) 17 February 1987 (1987-02-17) * example 6 * ---	1-16, 18	
A	US 5 073 623 A (STARK ERWIN ET AL) 17 December 1991 (1991-12-17) * example 1 * * claim 1 * * column 4, line 8 - line 22 * -----	1-8, 14-16, 18	
			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
			C08G C09D
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 16 August 1999	Examiner Paalman, R
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons S : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 40 1121

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

16-08-1999

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5021538 A	04-06-1991	NONE	
EP 0769538 A	23-04-1997	DE 19538954 A JP 9169912 A	24-04-1997 30-06-1997
US 4643848 A	17-02-1987	DE 3635145 A FR 2594837 A GB 2186881 A,B JP 1808324 C JP 5020470 B JP 62205175 A	27-08-1987 28-08-1987 26-08-1987 10-12-1993 19-03-1993 09-09-1987
US 5073623 A	17-12-1991	DE 3831242 A AT 116998 T DE 58908875 D EP 0361103 A ES 2066814 T JP 2175771 A JP 2818216 B	22-03-1990 15-01-1995 23-02-1995 04-04-1990 16-03-1995 09-07-1990 30-10-1998

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82